



MICROCOPY RESOLUTION TEST CHART NATIONAL BURGALLS COSTANGAR, 10 A (12) AROJ 14455.5-P

00 N 66 4D A 08

STUDIES OF PYROELECTRICITY

IN THIN SAMPLES OF FERROELECTRIC MATERIALS

FOR IMPROVED HIGH SPEED INFRARED DETECTORS.

9 FINAL REPORT. 1 Jun. 77-34 1116899

M. BASS AND M. SIMHONY

@Milled /Kinz Menden /Sinton/

DATE

15 SEPTEMBER 180

U.S. ARMY RESEARCH OFFICE

DAAG 29-77-G-0147 AND DAAG 29-79-C-0111-

INSTITUTION

CENTER FOR LASER STUDIES UNIVERSITY OF SOUTHERN CALIFORNIA

> APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED.

THE VIEW, OPINIONS AND / OR FINDINGS CONTAINED IN THIS REPORT ARE THOSE OF THE AUTHORS AND SHOULD NOT BE CONSTRUED AS AN OFFICIAL DEPARTMENT OF THE ARMY POSITION, POLICY, OR DECISION, UNLESS SO DESIGNATED BY OTHER DOCUMENTATION.

SECURITY CLASSIFICATION OF THIS PAGE (When Date Entered

REPORT DOCUMENTATION PAGE	READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER 14455-P AD-A089 95	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Supinio) STUDIES OF PYROELECTRICITY IN THIN SAMPLES OF FERROELECTRIC MATERIALS FOR IMPROVED HIGH SPEED	FINAL 1 June 1977 - 30 June 1980
INFRARED DETECTORS	6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(a)	Grant DAAG 29 77 G 0147
Dr. Michael Bass and Dr. Menahem Simhony	Contract DAAG 29 79 C 0111
9. PERFORMING ORGANIZATION NAME AND ADDRESS	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
Center for Laser Studies	AREA & WOME ONLY HOMEONIC
University of Southern California	
University Park, Los Angeles, CA 90007	12. REPORT DATE
11. CONTROLLING OFFICE NAME AND ADDRESS U. S. Army Research Office	15 September1980
Post Office Box 12211	13 NUMBER OF PAGES
Research Triangle Park, NC 27709	4
14. MONITORING AGENCY NAME & ADDRESS(II different from Controlling Office)	15. SECURITY CLASS, (of this report)
!	Unclassified
	15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report)	

Approved for public release; distribution unlimited.

17. DISTRIBUTION STATEMENT (of the abelract entered in Block 20, if different from Report)

NA

18. SUPPLEMENTARY NOTES

The view, opinions, and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.

second pulse detectors. Incubation time of piezoelectric oscillations in pyroelectric detectors. Space-charge injection component of poling currents in thin RLZT samples. Measurement of pyroelectric coefficient under poling.

Pyroelectric (PE) detectors made of 10 and 25 µm thick samples of PLZT 8/65/35 respond well to megawatt, 50 nsec CO₂ laser pulses. Superimposed piezoelectric oscillations have an incubation time, during which they do not disturb the PE response. Edge-electroded detectors showed an RC time of 60 picosecond. Poling currents in the samples appear to have components due to space-charge injection and to solaron formation and motion. A method was developed to separate the PE component of the poling current and to measure the PE coefficient under the poling voltage.

DO 1 140 79 1473 EDITION OF 1 NOV 65 IS OBSOLETE

UNCLASSIFIED
SECURITY CLASSIFICATION OF THIS PAGE (From 20 & Eric od)

A. Statement of Problem Studied

The problem studied was pyroelectricity in thin samples of ferroelectric materials. Most of our work was done on 10 μm and 25 μm thick samples of the ceramic PLZT 8/65/35. We studied the poling currents in the samples, their dependence on the poling voltage and the temperature treatment. We analyzed the pyroelectric responses of the samples to short (50 nsec) megawatt ${\rm CO}_2$ laser pulses and the accompanying piezoelectric oscillations. We have also started to work on a better sample geometry for the detection of sub-one hundred psec laser pulses.

B. Summary of the Most Important Results

- 1.) We have proven the applicability of the PLZT 8/65/35 ceramic for the detection of infrared laser pulses. Thin samples of PLZT are easier to prepare than those of LiTaO3 or SBN and they withstand powerful laser pulses (2 MW/cm²) with less damage. PLZT detectors with edge electrodes respond well to the sub-one hundred psec pulses of the Los Alamos CO2 laser. They showed a 60 psec characteristic RC time and a 1-3 volt/MW responsivity. These preliminary results can be improved by increasing the absorbtivity of the detectors and improving the poling procedures.
- 2.) We have shown that the piezoelectric oscillations which are usually superimposed on the pyroelectric (PE) voltage response to radiation signals have an incubation time, i.e., they start after the beginning of the PE response. During the incubation time (40-60 nsec in our samples) the PE response is not disturbed.

Thus, PE detectors for short laser pulses can be designed with minimum piezoelectric interference. 2,4

- 3.) We have developed a method of measuring the PE coefficient under the poling voltage in the presence of non-pyroelectric currents, by applying short pulses of heating or cooling. 6 The method can be important for monitoring the stage of poling in the production of pyroelectric detectors.
- 4.) We have found that the poling currents in PLZT samples are partially caused by injection of free charge, and are space-charge limited. 6,7 We have also considered the contribution to the poling currents of polaron formation and motion. 7

- C. LIST OF PARTICIPATING SCIENTIFIC PERSONNEL
- 1. Dr. Michael Bass, Principal Investigator, 1977-1980.
- 2. Dr. Menahem Simhony, Senior Investigator, 1977-1980.
- 3. Dr. E.W. Van Stryland, Measurements with Mode-Locked TEA CO₂ Laser, May-August 1978.
- 4. Dr. E.M. Tenescu, Measurement of Poling Currents, Feb. 1978-Jan. 1979.
- 5. Benjamin Levy, Blackbody Responsivity Measurements in PLZT

 Samples After Using Different Poling Procedures, April
 September 1978/ (Part of M.Sc. thesis work in Applied Physics;

 degree granted by the Hebrew University, Jerusalem).

D. LIST OF PUBLICATIONS Submitted and Published Under this ARO Project

- Fast Response of PLZT Pyroelectric Detectors to Megawatt CO₂
 Laser Pulses, M. Simhony, M. Bass, E.W. Van Stryland,
 E.M. Tenescu, IEEE J. Quantum Electronics, QE-15 (1979) 206-208.
- Piezoelectric Oscillations in PLZT Pyroelectric Detectors in Response to Short CO₂ Laser Pulses, M. Simhony, and M. Bass, Appl. Phys. Letters 34 (1979) 426-427.
- Peculiarities in the Electrical Conductivity and Pyroelectric Behavior of Thin Samples of PLZT 8/65/35, M. Simhony,
 E.M. Tenescu and M. Bass, Ferroelectrics 28 (1980) 391.
- 4. Delayed onset of piezoelectric oscillations in PLZT Pyroelectric Detectors, M. Simhony, Ferroelectrics 28 (1980) 373-376.
- 5. Measurement of the Pyroelectric Coefficient and Permittivity on Rhododendron and Encephalartos Leaves and on the Insect Periplaneta Americana, M. Simhony and H. Athenstaedt, Biophys. J. 29 (1980) 331-338.
- 6. Measurement of the Pyroelectric Coefficient from Poling
 Currents in Thin PLZT Samples Under Possible Injection of
 Free Charge, M. Simhony, Ferroelectrics (1980).
- 7. Measurement of Electric Charge, Current and Pyroelectric Coefficient in Thin PLZT Samples under Poling, M. Simhony, submitted to Ferroelectrics.